


D-20743-1

- 2 -

CLAIMS

1. (Previously presented) A process for selectively adsorbing a component of a gas mixture, which comprises contacting the mixture with a solid state, selective adsorbent material comprising a porous framework of a plurality of transition element complexes (TECs) having the formula shown below.



wherein:

- (a) M is a primary transition metal ion;
- (b) D to D_4 are primary donors and m is zero or one, at least three of D to D_4 occupying primary donor coordination sites on M but leaving at least one open coordination site on M for the component to react with M ;
- (c) G to G_4 are functional groups and n is zero or one, at least one of G to G_4 being intramolecularly bonded to at least three adjacent primary donors to form at least one 5 or 6 member chelate ring on the primary transition metal ion and providing at least three donors thereto;

D-20743-1

- 3 -

(d) M, D to D₄ and G to G₄ together define one or more transition metal complexes, wherein said complexes are the same or different and wherein k is from 0 to 4;

(e) R is an intermolecular connecting group selected from

- (i) secondary metal ions coordinated with secondary donors bonded to one or more of groups G to G₄ on the respective TECs;
- (ii) multifunctional organic groups forming covalent bonds with one or more of groups G to G₄ on the respective TECs; or
- (iii) non-coordinating counter-ions spaced between and separating the respective TECs;

wherein z is from 1 to 8, and wherein R may be the same or different when z is greater than 1; and

(f) y is an integer sufficient to provide said porous framework of the plurality of TECs for the selective adsorption of the desired component thereon.

2. (Original) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein said transition metal ion M is an element selected from the first, second or third row of transition metals of the Periodic Table and the lanthanides.

3. (Original) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein the donors D to D₄ are N, O, S, C, P, Cl, F, or Br, and may be neutral or charged.

4. (Original) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein G to G₄ may be the same or different and are:

- a) pyridinyl or imidazolyl groups;
- b) amino groups having the formula -NR¹R²R³;
- c) imino groups having the formula -R¹N=CR²R³ or -N=CR¹R²;
- d) carbonyl groups having the formula -R¹C(O)R²,
-R¹CONR²R³ or -R¹CO₂R²;
- e) cyano groups having the formula -R¹-CN;
- f) nitro groups having the formula -R¹-NO₂;

D-20743-1

- 4 -


g) phenolate groups with up to five substituents selected from halogens or -R¹;

h) carboxylate groups having the formula -R¹CO₂⁻; and

i) alkoxy groups having the formula -R¹O⁻;

wherein R¹, R² and R³ are the same or different and are substituted or unsubstituted acyclic or carbocyclic groups, or substituted by F, Cl, Br, O, N, P, S, Si or B.

5. (Original) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein R is a member of group (i) and has the structure



wherein D' is a secondary donor or a group of 2 to 4 secondary donors bonded to at least a G₄ group or a chelate ring on a coordination site on M and may also bond to an adjacent R group within the porous framework; and M' is a secondary metal ion coordinated with secondary donors D', x is from 0 to 6 and z is from 1 to 8; said structure bonding the respective TECs to one another to form said porous framework.


6. (Original) The process of claim 5 for selectively adsorbing a component of a gas mixture, wherein the TECs are Co(Me₂Ac₂H₂malen)(4-Py-O⁻).

7. (Original) The process of claim 5 for selectively adsorbing a component of a gas mixture, wherein the TECs are Co(Me₂Ac₂H₂maltmen)(4-Py-O⁻).

8. (Previously presented) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein R is a member of group (ii) and has the formula

D-20743-1

- 5 -



or mixtures thereof, and wherein R^1 is a substituted or unsubstituted acyclic or carbocyclic group and is unsubstituted or is substituted by F, Cl, Br, O, N, P, S, Si or B.

9. (Original) The process of claim 8 for selectively adsorbing a component of a gas mixture, wherein the TEC is $\text{Co}(\text{Me}_2\text{H}_2\text{malophen})\text{Py}$.

10. (Previously presented) A process for selectively adsorbing a component of a gas mixture, which comprises contacting the mixture with a solid state, selective adsorbent material comprising a porous framework of a plurality of transition element complexes (TECs) having the formula shown in Figure 1:, wherein:

- (a) M is a primary transition metal ion;
- (b) D to D_4 are primary donors and m is zero or one, at least three of D to D_4 occupying primary donor coordination sites on M but leaving at least one open coordination site on M for the component to react with M;
- (c) G to G_4 are functional groups and n is zero or one, at least one of G to G_4 being intramolecularly bonded to at least three adjacent primary donors to form at least one 5 or 6 member chelate ring on the primary transition metal ion and providing at least three donors thereto;

D-20743-1

- 6 -

(d) M, D to D₄ and G to G₄ together define one or more transition metal complexes, wherein said complexes are the same or different and wherein k is from 0 to 4; and

(e) selectively adsorbing a component of a gas mixture, wherein R is a member of group (iii) and is selected from:

- (i) an amide group having the formula R¹CONR²-;
- (ii) an amino group having the formula R¹R²n-;
- (iii) a carbinol group having the formula -R¹OH; or
- (iv) a carboxylic acid group having the formula -R¹CO₂H,

wherein R¹ and R² are the same or different and are unsubstituted acyclic or carbocyclic groups, or substituted acyclic or carbocyclic groups substituted by F, Cl, Br, O, N, P, S, Si or B.

11. (Original) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein R is a member of group (iv), selected from:


(a) an alkylammonium or arylammonium cation having the formula-(R¹R²R³R⁴)N⁺, wherein R¹R²R³ and R⁴ are the same or different and are hydrogen and at least one of which is an unsubstituted acyclic or carbocyclic group or an acyclic or carbocyclic group substituted by F, Cl, Br, O, N, P, S, Si or B when the TECs are anionic; or

(b) BF₄-, BOR⁻, PF₆-, NO₃-, SO₄²⁻, CO₃²⁻, MoO₄²⁻, a polyoxometallate, R⁻CO₂-, R⁻O-, R⁻SO₃-, wherein R⁻ is a C₁₋₂₀ alkyl or an aryl or hetero group having from 4 to 20 carbon atoms, when the TECs are cationic.

12. (Previously presented) A process for selectively adsorbing oxygen from a gas mixture, which comprises contacting the mixture with a solid state, selective adsorbent material comprising a porous framework of a plurality of transition element complexes (TECs) having the formula shown below,

D-20743-1


- 7 -



- (a) M is a primary transition metal ion selected from Co(II), Fe(II) or Mn(II);
- (b) D to D_4 are primary donors occupying primary donor coordination sites on M but leaving one open coordination site on M for an oxygen molecule to react with M ;
- (c) G to G_4 are functional groups and n is zero or one, at least one of G to G_4 being intramolecularly bonded to at least three adjacent primary donors to form at least one 5 or 6 member chelate ring on the primary transition metal ion and providing at least three donors thereto;
- (d) M, D to D_4 and G to G_4 together define one or more transition metal complexes TEC A, TEC B and TEC C, wherein said complexes are the same or different;
- (e) D' is a secondary donor or a group of secondary donors bonded to a chelate ring on a coordination site on M ;
- (f) M' is a secondary metal ion coordinated with secondary donors D' ;

D-20743-1


- 8 -



the group bonding the respective TECs to one another to maintain them in a porous framework and wherein z is from 1 to 8 and x is from 0 to 6; and

(g) y is an integer sufficient to provide said porous framework of the plurality of TECs for the selective adsorption of oxygen thereon.

13. (Previously presented) A process for selectively adsorbing a component of a gas mixture, which comprises contacting the mixture with a solid state, selective adsorbent material comprising a porous framework of a plurality of transition element complexes (TECs) having the formula shown below.



D-20743-1

- 9 -


wherein:

- (a) M is a primary transition metal ion;
- (b) D to D₄ are primary donors and m is zero or one, at least three of D to D₄ occupying primary donor coordination sites on M but leaving at least one open coordination site on M for the component to react with M;
- (c) G to G₄ are functional groups and n is zero or one, at least one of G to G₄ being intramolecularly bonded to at least three adjacent primary donors to form at least one 5 or 6 member chelate ring on the primary transition metal ion and providing at least three donors thereto;
- (d) M, D to D₄ and G to G₄ together define one or more transition metal complexes, wherein said complexes are the same or different and wherein k is from 0 to 4;
- (e) R is an intermolecular connecting group selected from
 - (i) secondary metal ions coordinated with secondary donors bonded to one or more of groups G to G₄ on the respective TECs;
 - (ii) multifunctional organic groups forming covalent bonds with one or more of groups G to G₄ on the respective TECs;
 - (iii) non-coordinating counter-ions spaced between and separating the respective TECs;

wherein z is from 1 to 8, and wherein R may be the same or different when z is greater than 1; and

- (f) y is an integer sufficient to provide said porous framework of the plurality of TECs for the selective adsorption of the desired component thereon.

14. (Currently amended) The ~~composition~~ process of claim 13 for selectively adsorbing a component of a gas mixture, wherein R is a member of group (i) and has the structure





D-20743-1

- 10 -


wherein D' is a secondary donor or a group of two to four secondary donors bonded to a chelate ring on a coordination site on M but may also bond to an adjacent R group within the porous framework; and M' is a secondary metal ion coordinated with secondary donors D', wherein z is from 1 to 8 and x is from 0 to 6; said structure bonding the respective TECs to one another to form said porous framework.

15 (Currently amended) The ~~composition process~~ of claim 14 for selectively adsorbing a component of a gas mixture, wherein the TECs are $\text{Co}(\text{Me}_2\text{Ac}_2\text{H}_2\text{malen})(4\text{-Py-O}^-)$ or $\text{Co}(\text{Me}_2\text{Ac}_2\text{H}_2\text{maltmen})(4\text{-Py-O}^-)$.

16. (Currently amended) The ~~composition process~~ of claim 13 for selectively adsorbing a component of a gas mixture, wherein R is a member of group (ii) and has the formula



|



or mixtures thereof, wherein R¹ is a substituted or unsubstituted acyclic or carbocyclic group and is unsubstituted or is substituted by F, Cl, Br, O, N, P, S, Si or B.

D-20743-1

- 11 -

17. (Currently amended) The ~~composition~~ process of claim 16 for selectively adsorbing a component of a gas mixture, wherein the TECs are $\text{Co}(\text{Me}_2\text{H}_2\text{H}_2\text{malophen})\text{Py}$.

18. (Currently amended) The ~~composition~~ process of claim 16 for selectively adsorbing a component of a gas mixture, wherein the TECs are $\text{Co}(\text{Me}_2\text{H}_2\text{H}_2\text{maltmen})(4\text{-PyOLi})$.

19. (Currently amended) The ~~composition~~ process of claim 16 for selectively adsorbing a component of a gas mixture, wherein the TECs are $\text{Co}(\text{Me}_2\text{H}_2\text{H}_2\text{maldmen})(4\text{-PyOLi})$.

20. (Previously presented) A composition for selectively adsorbing a component of a gas mixture which comprises a solid state, selective adsorbent material comprising a porous framework of a plurality of transition element complexes (TECs) having the formula shown in Figure 1, wherein:

- (a) M is a primary transition metal ion;
- (b) D to D_4 are primary donors and m is zero or one, at least three of D to D_4 occupying primary donor coordination sites on M but leaving at least one open coordination site on M for the component to react with M;
- (c) G to G_4 are functional groups and n is zero or one, at least one of G to G_4 being intramolecularly bonded to at least three adjacent primary donors to form at least one 5 or 6 member chelate ring on the primary transition metal ion and providing at least three donors thereto;
- (d) M, D to D_4 and G to G_4 together define one or more transition metal complexes, wherein said complexes are the same or different and wherein k is from 0 to 4;
- (e) selectively adsorbing a component of gas mixtures wherein R is a member of group (iii) and is selected from:
 - (i) an amide group having the formula R^1CONR^2 —;
 - (ii) an amino group having the formula $\text{R}^1\text{R}^2\text{n}$ —;
 - (iii) a carbinol group having the formula $-\text{R}^1\text{OH}$; or
 - (iv) a carboxylic acid group having the formula $-\text{R}^1\text{CO}_2\text{H}$.

D-20743-1

- 12 -

wherein R¹ and R² are the same or different and are unsubstituted acyclic or carbocyclic groups, or substituted acyclic or carbocyclic groups substituted by F, Cl, Br, O, N, P, S, Si or B.

21. (Currently amended) The ~~composition~~ process of claim 13 for selectively adsorbing a component of a gas mixture, wherein R is a member of group (iv), selected from:

- (a) an alkylammonium or arylammonium cation having the formula - (R¹R²R³R⁴)N⁺, wherein R¹, R², R³ and R⁴ are the same or different and are hydrogen and at least one of which is an unsubstituted acyclic or carbocyclic group or an acyclic or carbocyclic group substituted by F, Cl, Br, O, N, P, S, Si or B when the TECs are anionic; or
- (b) BF₄⁻, BOR₃⁻, PF₆⁻, NO₃⁻, SO₄²⁻, CO₃²⁻, MoO₄²⁻, a polyoxometallate, R''CO₂⁻, R''O⁻, R''SO₃⁻, wherein R'' is a C₁₋₂₀ alkyl or an aryl or hetero group having from 4 to 20 carbon atoms, when the TECs are cationic.

22. (Previously presented) The process of claim 1 for selectively adsorbing a component of a gas mixture, wherein said TECs are Co(Me²H²H²maldmen) (4-PyOLi).

23. (Previously presented) The process of claim 1, wherein R is a member of group (i), and said secondary metal ions are selected from the group consisting of: Li⁺, Na⁺, K⁺, Rb⁺, Cs⁺, Be²⁺, Mg²⁺, Ca²⁺, Sr²⁺, Ba²⁺, B³⁺, Al³⁺, Ga³⁺, In³⁺, Ti³⁺, Sn²⁺, Sn⁴⁺, Pb²⁺, Sb⁴⁺, Sc³⁺, Ti³⁺, V³⁺, Cr³⁺, Mn²⁺, Fe²⁺, Co²⁺, Ni²⁺, Cu²⁺, Zn²⁺, Y³⁺, Ru³⁺, Pd²⁺, Ag⁺, Cd²⁺, lanthanides, Pt²⁺, Au³⁺ and Hg²⁺.

24. (Previously presented) The process of claim 22, wherein R is a member of group (i), and said secondary donors are selected from the group consisting of: O, N, S, Cl, F, Br, I, C, and P.

25. (Previously presented) The process of claim 12, said secondary metal ion is selected from the group consisting of: Li⁺, Na⁺, K⁺, Rb⁺, Cs⁺, Be²⁺, Mg²⁺, Ca²⁺, Sr²⁺, Ba²⁺, B³⁺,

D-20743-1

- 13 -

Al^{3+} , Ga^{3+} , In^{3+} , Ti^{3+} , Sn^{2+} , Sn^{4+} , Pb^{2+} , Sb^{4+} , Sc^{3+} , Ti^{3+} , V^{3+} , Cr^{3+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Ni^{2+} , Cu^{2+} , Zn^{2+} , Y^{3+} , Ru^{3+} , Pd^{2+} , Ag^{+} , Cd^{2+} , lanthanides, Pt^{2+} , Au^{3+} and Hg^{2+} .

26. (Previously presented) The process of claim 24, said secondary donor is selected from the group consisting of: O, N, S, Cl, F, Br, I, C, and P.

27. (Previously presented) The process of claim 13, wherein R is a member of group (i), and said secondary metal ions are selected from the group consisting of: Li^{+} , Na^{+} , K^{+} , Rb^{+} , Cs^{+} , Be^{2+} , Mg^{2+} , Ca^{2+} , Sr^{2+} , Ba^{2+} , B^{3+} , Al^{3+} , Ga^{3+} , In^{3+} , Ti^{3+} , Sn^{2+} , Sn^{4+} , Pb^{2+} , Sb^{4+} , Sc^{3+} , Ti^{3+} , V^{3+} , Cr^{3+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Ni^{2+} , Cu^{2+} , Zn^{2+} , Y^{3+} , Pd^{2+} , Ag^{+} , Cd^{2+} , lanthanides, Pt^{2+} , Au^{3+} and Hg^{2+} .

28. (Previously presented) The process of claim 26, wherein R is a member of group (i), and said secondary donors are selected from the group consisting of: O, N, S, Cl, F, Br, I, C, and P.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.